



SAFRA Al.Mg.5/ER 5356

A.W.S. /ASTM A5.10:
ER 5356

DIN EN ISO 18273:
S Al 5356-AlMg5Cr A

DESCRIPTION

Aluminium wires and rods for welding alloys with aluminium and magnesium basis, with maximum 5% Magnesium. High corrosion resistance.

Applications in the construction of ships, storage tanks, railways and in the automotive industry.

CHEMICAL COMPOSITION

Al remainder

Si <0,25

Fe <0,40

Cu <0,10

Mn 0,05 - 0,20

Mg 4,5 - 5,5

Cr 0,05 - 0,20

Zn <0,10

Ti 0,06 - 0,20

Be <0,0003

OTHERS EACH <0,05

OTHERS TOTAL <0,15

MATERIALS TO BE WELDED

Al Mg 3	Al Mg 5	Al Mg Mn	Al Zn Mg 1	G-Al Mg 3 Si	G-Al Mg 5 Si	G-Al Mg 10
Al Mg 1 Si Cu	Al Mg Si 0,7					

SHIELDING GASES FOR GMAW/GTAW

Ar 99,99% min.
Ar 75% + He 25%
Ar 50% + He 50%

MINIMAL VALUES OF THE MECHANICAL PROPERTIES (WELDED METAL)

Tensile strenght Rm: 240 N/mm²
Yeld strenght Rp 0,2: 110 N/mm²
Elongation L=5d: 17%

AVAILABLE SIZES

MIG: 6-7 Kg D300 or K300/KS300 Spools

TIG carton box of 10 kg
(x 1000 mm length)

DIAMETER OF THE WIRE

0,8 mm - 1,0 mm - 1,2 mm - 1,6 mm - 2,0 mm - 2,4 mm

DIAMETER OF THE RODS

1,6 mm-2,0 mm-2,4 mm-3,2 mm-4,0 mm-5,0 mm

MINI-MIG 0,5 Kg D100 Spools

DIAMETER OF THE WIRE

0,8 mm - 1,0 mm - 1,2 mm

MORE DIAMETERS AND PACKAGING UPON REQUEST