



SAFRA Al.Si.12/ER 4047

A.W.S./ASTM A5.10:
ER 4047

DIN EN ISO 18273:
S Al 4047 A - Al Si 12 A

DESCRIPTION

Aluminium wires and rods for welding and brazing.

Good mechanical characteristics: its excellent corrosion resistance and low melting point ensure a very low number of deformations in the parent metal. This material is generally used for brazing aluminium sheets, for extrusions and castings.

(After anodizing the welding will be of a different colour).

CHEMICAL COMPOSITION

Al remainder

Si 11,0 - 13,0

Fe <0,60

Cu <0,30

Mn <0,15

Mg <0,10

Zn <0,20

Ti <0,15

Be <0,0003

OTHERS EACH <0,05

OTHERS TOTAL <0,15

MATERIALS TO BE WELDED

G-Al Si 10 Mg | G-Al Si 11 | G-Al Si 12 (Cu) | G-Al Si 7 Mg | G-Al Si 6 Cu 4 | Al Mg Si 0.8 | Al Mg Si 1

(use flux when brazing oxyacetylene).

SHIELDING GASES FOR GMAW/GTAW

Ar 99,99% min.

MINIMAL VALUES OF THE MECHANICAL PROPERTIES (WELDED METAL)

Tensile strenght Rm:	130 N/mm ²
Yeld strenght Rp 0,2:	60 N/mm ²
Elongation L=5d:	5%
Melting range:	573-585°C

AVAILABLE SIZES

MIG: 6-7 Kg D300 or K300/KS300 Spools

TIG carton box of 10 kg
(x 1000 mm length)

DIAMETER OF THE WIRE

0,8 mm - 1,0 mm - 1,2 mm - 1,6 mm - 2,0 mm - 2,4 mm

DIAMETER OF THE RODS

1,6 mm-2,0 mm-2,4 mm-3,2 mm-4,0 mm-5,0 mm

MORE DIAMETERS AND PACKAGING UPON REQUEST